

**ENDURATHANE 245/60 (CFC FREE)**  
RIGID FOAM MOULDING SYSTEM

**DESCRIPTION**

**ENDURATHANE 245/60 is a medium density rigid polyurethane moulding foam** suitable for handpour or machine application.

Frequently referred to as structural polyurethane foam, the prime characteristic is a sandwich structure consisting of a microscopic cellular core and discreet non-cellular surface layers. The core and surface layers consist of one and the same material and are formed in a single operation (ie not laminates). The properties of these foams can be tailored readily to a wide variety of end-uses by variation of the chemistry of the components or of the processing conditions. This is achieved far more easily than is possible for comparable systems such as thermoplastics.

**RECOMMENDED USES**

The combination of smooth, hard skins and good mechanical properties at low gross weights coupled with good processing characteristics and wide design freedom, makes ENDURATHANE 245/60 ideal for applications such as decorative and ornamental mouldings, furniture, wall-panelling (wood grain reproduction) panel doors, ornamental legs, decorative drawer fronts and cupboard doors, and many other conventionally wooden products.

Foaming pressures are very low and moulds are lighter and less expensive than those used for thermoplastic injection moulding.

**PHYSICAL PROPERTIES**

**Components**

Component A (isocyanate)  
 Viscosity (20°C) ..... 200 cps  
 Flashpoint (ASTM D92) ..230°C Specific Gravity ..... 1.25  
 Component B (polyol)  
 Viscosity (20°C) .....6200cps  
 Specific Gravity ..... 1.08

**Reaction Profile**

Cream Time (20°C) ..... 60 secs  
 Rise Time .....120 secs  
 Tack Free Time .....240 secs

**Mix Ratio**

115:100 parts by weight  
 100:100 parts by volume

**Cured Foam**

Density ..... 250 kg/m<sup>3</sup>  
 Thermal Conductivity ..... 0.048  
 (Kcal/m<sup>2</sup> hr°C)  
 Compressive Strength (kN/m<sup>2</sup>)  
 Free rise ..... 5000  
 Moulded (overpacked 20%) 9000  
 Closed Cells ..... 90 - 95%  
 Dimensional Stability  
 24 hrs @ 100°C ..... 1 to 2%  
 24 hrs @ -40°C ..... 0%  
 24 hrs @ 70°C/100% RH 0 to 2%  
 Water Absorption  
 (%ASTM D2842) .....≤0.5  
 Water Absorption  
 (Perm-in ... ASTM C-355 @ 23°C)

To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact Polymer Group Ltd. to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Polymer Group Ltd. quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. Prices and cost data if shown, are subject to change without prior notice. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OR LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

## APPLICATION DATA

**ENDURATHANE 245/60** can be hand mixed (see separate application bulletin) or machine-applied through 2-component polyurethane application equipment such as **Glas-Craft Probler** or similar.

Please consult your representative for advice regarding any equipment application questions you may have.

### Equipment: Glas-Craft Probler

Pre-heat Part A [isocyanate] 45°C

Part B [polyol] 60°C

Hose Temperature: 40-50°C

Optimum temperatures will vary with equipment, substrate temperature and ambient conditions generally.

Check and maintain correct output ratio to  $\pm 2\%$ .

Ensure metering is accurate by regular ratio checks and monitoring of line pressures to gun. Operator must have adequate product knowledge to recognise faulty foam so remedial action can be taken.

### Mould Materials:

**Endurathane 245/60** may be used with most common mould materials. Substrates must be clean and dry.

**Ambient and surface temperatures** should be above 15°C (moulds are usually run in the 30-40°C range). **Low temperatures will decrease rise of foam markedly.** Suitable release agents must be used.

### Theoretical Yield:

Always check yield and application rates. Adequate allowance must be made for overpacking, especially when cavities are narrow or foam has a long flow path.

1 kg of foam occupies 0.004 cu. m.

### Handling Precautions:

**All chemical materials should be used by trained personnel.**

**Component A [isocyanate]** contains methylenebisphenyldiisocyanate [MDI]. It is an irritant and allergic sensitizer. It is moderately toxic. **Avoid contact with skin or eyes, avoid breathing vapour** and use only in well ventilated areas.

Always wear **eye protection** and suitable **protective clothing.**

**Flush splashes to the skin or eyes with copious quantities of water.**

### Clean up:

Owing to the chemical resistance of polyurethane products it is important to clean up any surplus as quickly as possible. Methyl Proxitol is suitable for general cleaning and methylene chloride can be used as a line flush.

**Wear suitable protective clothing, goggles and gloves at all times when cleaning.**

Greasing components beforehand assists with contamination removal.

### Storage:

Store at temperatures between 15° and 26°C in tightly closed containers to prevent moisture and other contamination. If exposed to moisture Component A will crystallise resulting in line blockages.

**Shelf Life:** Minimum 6 months.

14.12.09 replaces Mar 04

## POLYMER GROUP LTD

PO Box 204 106, Highbrook, Auckland 2161, New Zealand

Telephone: 64-9-274 1400 Fax: 64-9-274 1405

Email: [sales@polymer.co.nz](mailto:sales@polymer.co.nz) [www.polymer.co.nz](http://www.polymer.co.nz)