

**ENDURATHANE 3225-100R  
INJECTION FOAM SYSTEM - CFC FREE**

**DESCRIPTION:**

**ENDURATHANE 3225-100R rigid polyurethane foam** is a new generation high performance rigid polyurethane foam, with dual gas blowing mechanism especially designed for machine injection applications.

**ENDURATHANE 3225-100R** is a low density, general purpose buoyancy and insulation foam. It is a fire retarded grade with good self-extinguishing properties, coupled with low thermal conductivity and permeability, good mechanical strength, chemical resistance and dimensional stability.

**RECOMMENDED USES:**

**Applications include:-**

- Wall and door cavity insulation
- Roof insulation/refurbishment
- Pipe insulation, panel filling
- Marine buoyancy compartments
- Refrigerated display cabinets
- Walk-in coolers/freezers
- Fish holds & freezers
- Insulated building panels
- Refrigerated transport trailers
- Refrigerated containers
- Laminated composites for:-
  - light weight spandrels
  - low cost insulation boards
  - roofing panels

**PHYSICAL PROPERTIES:**

**Components:**

Component A (isocyanate)	
Viscosity (20°C)	200cps
Flashpoint (ASTM D92)	230°C
Specific Gravity	1.24
Component B (polyol)	
Viscosity (20°C)	400cps
Specific Gravity	1.15

**Reaction Profile:**

Cream Time (20°C)	25 secs
Rise Time	100
secs	
Tack Free Time	125 secs

**Mix Ratio:**

100:100 parts by volume  
108:100 parts by weight

**Overpack allowance:**

Normal overpack factors may range from 10-50% dependent on final density required.

**Cured Foam:**

Density, free rise	32 kg/m <sup>3</sup>
Thermal Conductivity (Kcal/m <sup>2</sup> hr °C)	0.019-0.023
Compressive Strength	150 kN/m <sup>2</sup>
Closed Cells	90-95%
Dimensional Stability	
24 hrs @ 100°C	1 to 5%
24 hrs @ -40°C	0%
24 hrs @ 70°C/100% RH	0 to 5%
Water Absorption (23°C,kg/m <sup>2</sup> )	0.49
Water Vapour Permeability (Perm-in - ASTM C-355 @ 23°C)	1.8
Flammability	
DIN 4102	B3 rating
ASTM D-1692	Self extinguishing

**NOTE:** As polyurethane foam products may constitute a serious fire hazard if improperly used or protected, a careful assessment should be made to determine what potential hazard may exist.

Nov 09 replaces July 04

To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact Polymer Group Ltd. to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Polymer Group Ltd. quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. Prices and cost data if shown, are subject to change without prior notice. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OR LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

## APPLICATION DATA

ENDURATHANE 3225-100R should be machine-applied through 2-component polyurethane application equipment such as **Glas-Craft Probler** or similar. Please consult your representative or our Contracts Manager for advice regarding any equipment application questions you may have.

**Equipment:** **Glas-Craft Probler**

Pre-heat: Part A [isocyanate] 45°C  
Part B [polyol] 45°C  
Hose Temperature: 40-50°C  
Optimum temperatures will vary with equipment, substrate temperature and ambient conditions generally. Check and maintain correct output ratio to  $\pm 2\%$ . Ensure metering is accurate by regular ratio checks and monitoring of line pressures to gun. Operator must have adequate product knowledge to recognise faulty foam so remedial action can be taken.

### **Substrates:**

Endurathane 3225-100R may be applied to most surfaces. Substrates must be clean and dry.

**Ambient and surface temperatures** should be above 15°C. **Low temperatures will decrease yield markedly.**

### **Theoretical Coverage:**

Always check yield and application rates at start of job and then regularly to ensure product usage is as expected. Pay special attention when applying on to a profiled substrate to determine the "flat" area. This can often be as much as 25% greater than the measured area. Similarly adequate allowance must be made for overpacking, especially when cavities are narrow or foam has a long flow path.

1 kg of foam occupies 0.032 cu.m [0.625 sq.m @ 50 mm] applied under ideal conditions [1 sq.m = 1.6 kg @ 50 mm].

## HANDLING PRECAUTIONS

**All chemical materials should be used by trained personnel.**

**Component A [isocyanate]** contains methylenebisphenyldiisocyanate [MDI]. It is an irritant and allergic sensitiser. It is moderately toxic. **Avoid contact with skin or eyes, avoid breathing vapour** and use only in well ventilated areas.

**Component B [polyol]** contains HCFC, a volatile blowing agent. It is a mild irritant. In confined spaces it may displace sufficient air to be hazardous. Provide ventilation or use only in well ventilated situations.

Always wear **eye protection** and suitable **protective clothing**.

**Flush splashes to the skin or eyes with copious quantities of water.**

### **Clean up:**

Owing to the chemical resistance of polyurethane products it is important to clean up any overspray as quickly as possible. Methyl Proxitol is suitable for general cleaning and methylene chloride can be used as a line flush.

Wear suitable protective clothing, goggles and gloves at all times when cleaning. Greasing components beforehand assists with contamination removal.

### **Storage:**

Store at temperatures between 15° and 26°C in tightly closed containers to prevent moisture and other contamination. If exposed to moisture Component A will crystallise resulting in line blockages.

**Shelf Life:** Minimum 6 months.

Nov 09 replaces July 04

---

## POLYMER GROUP LTD

PO Box 58256, Greenmount, Auckland 2141, New Zealand  
Telephone: 64-9-274 1400 Fax: 64-9-274 1405  
Email: sales@polymer.co.nz www.polymer.co.nz